

# tuforte<sup>®</sup> juntas



## TECHNICAL DATA SHEET

TOPECA, Lda  
Rua D. Nuno Alvares Pereira, 53  
2490-114 Cercal – Ourém  
PORTUGAL

Tel.: 00 351 – 249 580 070  
Fax.: 00 351 – 249 580 079

**TOPECA**  
FÁBRICA DE PRODUTOS PARA CONSTRUÇÃO

[geral@topeca.pt](mailto:geral@topeca.pt)  
[www.topeca.pt](http://www.topeca.pt)

# tuforte

## juntas

levelling and regularization

### jointing and finishing mortar



- drying;
- ref. normal: 2 hours;
- ref. slow: over 4 hours

## use

Jointing mortar for soft plaster board used in interiors.  
Allows bonding of bands and finishing of layers to be carried out.  
Fast hardening means that finishing can be achieved on same day, even in cold weather.

## surface

- Plaster board



## CE marking

3B  
European standards  
EN 13963

# tuforte juntas

jointing and finishing mortar

levelling and regularization

## recommendations

The paste cannot be used once it has started to harden.

Do not apply Tuforte Juntas in damp environments.

Tuforte Juntas when used as board barring can only be covered with film type finishes such as paint (after primer) and wall paper.

If you wish to cover the plaster board with a ceramic finish, the ceramic tiles must be bonded directly to the board, without Tuforte Juntas.

## composition and characteristics

### Composition:

Selected plaster, mineral fillers and specific additives.

### Characteristics:

Time paste can be used: 2 hours (reference: normal).

Time paste can be used: >4 hours (reference: slow).

Application temperature: >+5°C.

Density: 1.0.

Note: Results obtained in standard conditions according to EN 13963. These results may vary depending on application conditions.

## colour

White.

## consumption

0,3 a 0,35 Kg/m<sup>2</sup>.

## available in

Sacks of 20 kg.

Pallets with 48 sacks.

## storage

1 year from date of manufacture in a sealed packet stored in a damp free environment.



tuforte juntas  
jointing and finishing mortar

levelling and regularization

## preparation of surface

The surface must be clean and any screw heads must be countersunk and level on the board.



## application

Gradually pour the powder into approximately 14 litres of clean water and leave for 2 to 3 minutes.

Mechanically mix at a slow speed until an even and lump free paste is obtained.



With bands of paper or non-adhesive netting: fill the joints between boards and apply the band onto Tuforte Juntas. The frieze of the band is placed on the join of the two boards. Press well.



With adhesive netting: bond the netting band to the boards, centring the netting band on the join between the two boards. Apply Tuforte Juntas to the bands. Press well.



Cover the band again with a new layer of Tuforte Juntas. The mortar to cover the band must leave a thickness of approximately 10 cm to either side. If necessary, repeat the operation.

After the Tuforte Juntas has hardened, apply a general layer so as to provide a smooth finish.

