

# topeca endur classic



## TECHNICAL DATA SHEET

TOPECA, Lda  
Rua do Mosqueiro  
2490-115 Cercal – Ourém  
PORTUGAL

Tel.: 00 351 – 249 580 070  
Fax.: 00 351 – 249 580 079

**TOPECA**  
FÁBRICA DE PRODUTOS PARA CONSTRUÇÃO

[geral@topeca.pt](mailto:geral@topeca.pt)  
[www.topeca.pt](http://www.topeca.pt)

# topeca endur classic

decorative flooring

## hardener for screed floor



### uses

Topeca Endur Classic is a mixture which can be applied to the surface of screed to give it a smooth, colourful finish.

Produces a finish is similar to polished concrete.

Product can be applied manually without using a power trowel (helicopter).

Topeca Endur Classic can be applied to freshly screed.

It can be used in residential, commercial etc.

It is an affordable system thanks to its low maintenance costs and long life.

Resistant to wear and tear.

Reduces costs and saves time.

Highly durable.

It helps to stop dust forming.

### surfaces

- Fresh screed.



TOPECA, Lda - Rua do Mosqueiro - 2490-115 Cercal – Ourém - PORTUGAL

Tel.: 00 351 – 249 580 070 / Fax.: 00 351 – 249 580 079

[www.topeca.pt](http://www.topeca.pt) / [geral@topeca.pt](mailto:geral@topeca.pt)

Q.5.06.06.02-02

23/08/2016

# topeca endur classic

hardener for screed floor

decorative flooring

## recommendations

Leave a joint between the perimeter wall and the floor, filling it with perimeter belt. If you want to revive / protect the color of the floor, you may do so by applying Silitop Wet or product range Topeca Floor.

To protect without changing the look of the floor, apply Silitop B3.

Protection products should be applied after complete healing of the screed and hardener (28 days).

## composition and characteristics

### Composition:

A mixture of aggregates of specifically selected sizes, cement and specific additives.

### Characteristics:

Waiting time before it can be:

- walked on: 1 to 2 days;
- used normally: 28 days.

Reaction to fire: Class A1.

Note: These results were obtained in laboratory tests, under standard conditions, and may vary with changes in temperature and depending on the type of material to which the product is applied.

## colour

Grey, red, green, anthracite, beige.

## consumption

Manual Application: 1,5 - 2kg / m<sup>2</sup>  
(as an indication).

Mechanical Application: 3-4 kg / m<sup>2</sup>  
(as an indication).

## available in

Sacks – 25kg and 10kg.

Pallet - 48 sacks (sacks with 25kg).

## storage

1 year from the date of manufacture, kept closed in the original packaging and protected from damp, heat and extreme cold.



# topeca endur classic

hardener for screed floor

decorative flooring

## preparation of surface

The screed should be rich in cement (stroke volume indication, 1 cement: 3 sand washed) or Betonilha Cem, must have surface moisture, to allow proper wetting Topeca Endur Classic.

The screed should be sized to provide a suitable thickness for its use. The Topeca Endur Classic is applied on the fresh and moist screed.



## application

Programming work in small areas in order to make the application of the screed and hardener, without having to walk on the screed.

Apply the screed directly onto the support, go with scale and level to regulate. The screed is to be compacted and compressed to a smooth surface and having surface moisture.

The application of Topeca Endur Classic be performed immediately after the completion of the screed.



Spread, Topeca Endur Classic uniformly and homogeneously.

Wait until Topeca Endur Classic has been dampened by rising damp screed fresh.



Use a metal spatula or trowel (wet) to compress and smooth the Topeca Endur Classic.



# topeca endur classic

hardener for screed floor

decorative flooring

## associated products

- Silitop Wet - "wet effect" protection for natural stone;
- Topeca floor In / Out - Painted finish for flooring.
- Silitop B3 - Protector Water-Oil Repellent.

## colours



105812



109712




109512



109612



109812



109912